


## Microduct DuraMicro DB 12/8 mm

Microduct DuraMicro DB is intended for protection of optical microcables. Structural part (1) is made from high density polyethylene (HDPE). Inner surface (2) is made from permanent sliding material Sillicore™ with a very low coefficient of friction and standardly with fine ribs. Outer microduct's surface is smooth. Microduct is not designed for permanent inner pressure.



Wall thickness and material classify the microduct as a Direct Burial (DB). Installation methods and conditions are described in the Installation manual. The microduct can be supplied also as a part of bundles DuraFlat™ and DuraMulti.

- DURA-LINE CT's quality system is certified according to EN ISO 9001, EN ISO 14001 and OHSAS 18001.
- The microduct does not contain chemicals in accordance to the Directive of the European Parliament and the Commission no. 2006/1907/EC (REACH)
- The microduct meets requirements of the Directive of the European Parliament and the Commission no. 2011/65/EU (RoHS), as amended on January 3, 2013 (RoHS II).

The details to parameters are in company standard CWS 103-2015.

### DESCRIPTION, APPLICATION

### LEGISLATION

### PARAMETERS

Parameter	Value	Standard, conditions
Outer diameter (OD)	12±0,1 mm	CWS 103-2015
Inner diameter (ID)	min. 7,9 mm	CWS 103-2015
Wall thickness (WT)	min. 1,9 mm	CWS 103-2015
Ovality	max. 5%	CWS 103-2015, before coiling
Blown ball test (BB test)	pass	CWS 103-2015, ball diameter 6,5 mm
Inner coefficient of friction	max. 0,1	CWS 103-2015
Burst pressure	min. 60 bar	ČSN EN ISO 1167-1, 2
Visual examination	free from defects	CWS 103-2015
Crush - residual deformation	max. 15% OD = max. 1,8 mm	ČSN EN 60794-1-2. ed. 4, E3, sample 200mm, active 100mm, force 1 680 N, 3 mm/min., action 60 s, recovery 20 s
Crush - pressure force	min. 1 000 N	ČSN EN 60794-1-2. ed. 4, E3, sample 200mm, active 100mm, ID deformation by 15%, speed 3 mm/min.
Impact	no damage after the test, dimens. in tolerances after recovery	ČSN EN 60794-1-2. ed. 4, method E4, striking surface radius 10 mm, impact energy 15 J, recovery time 1 h
Bending stiffness	min. 0,36 N.m <sup>2</sup>	CWS 103-2015
Thermal expansion	*1,6.10 <sup>-4</sup> K <sup>-1</sup>	ISO 11359-2, temperature range from -20°C to +70°C
Longitudinal reversion	max. 3%	CSN EN ISO 2505, oven, 110°C, 60 min.
Standard Dimension Ratio (SDR = OD/WT)	*6	-
Weight	*59 kg/km	-
Transport and storage temperatures	from -40°C to +70°C	-
Installation temperatures	from -10°C to +50°C	-
Operating temperatures	from -40°C to +70°C	-
Installation tensile force	max. 840 N	-
Recommended cable dimens. for blowing	from 2,4 to 5,6 mm	-
Minimum bending radius	120 mm	-
Blowing pressure	max. 20 bar	max. 2 hours at max. +50°C
Outdoor exposure limit	max. 12 months	Central Europe conditions

\* informative value

## Microduct DuraMicro DB 12/8 mm

### MODIFICATION

- **Standard** is a basic material version convenient for most applications.
- **UV stabilized** is more resistant to ultraviolet radiation. Storability is prolonged to 24 months at Central Europe outdoor conditions.
- **Antistatic** - lower electrical surface resistance.
- **Antirodent** is more resistant to rodents because of special repellent additives.
- **Preinstalled pulling cord** with tensile strength min. 300 N.

### COLOR LIST

Microduct is supplied in natural translucent version or in wide scale of following RAL list. Longitudinal stripes with the same color are another possibility.



### MARKING

Microduct is printed in whole length according to customer requirement. Printing color is contrasting to microduct color. Printing can be doubled in opposite sides as an option. Printing scheme is repeating after 1 metre.

**Example of printing scheme:**

DURA-LINE CT DuraMicro DB 12/8 mm SILICORE 03/2009 LOT No 12345678 0000 m >|<

### PACKING AND STORAGE

Microduct is wound on disposable drum (MTB) and coil is wrapped by stretch film. Microduct's ends are protected by plastic caps protecting them from impurities penetrating into microduct. End of microduct is minimally 10 mm under the flange edge. MTB flanges are regularly made from chipboard and have to be protected from moisture.

Option - MTB flanges can be made from Oriented Strand Board (OSB) which is waterproof.

MTB core diameter is 415 mm.

All drum dimensions are informative values.

Drum width is measured near center in place of axis. The periphery width can be higher up to 10% because of pressure winded microducts.

Drum	Flange diameter (mm)	Drum width (mm)	Shaft hole diameter (mm)	Winding maximum length (m)	Informative weight of full drum with chipboard flanges (kg)
MTB2	600	640	65	500	40
MTB3	900	640	65	2 000	136
MTB7	1 000	550	82	2 000	140
MTB8	1 030	640	65	2 600	177
MTB9	1 000	510	82	1 850	128
MTB12	1 030	640	82	2 600	177
MTB13	1 190	510	82	3 000	213